





Q.ANTUM DUO Z Technology with zero gap cell layout boosts module efficiency up to 21.1%.



THE MOST THOROUGH TESTING PROGRAMME IN THE INDUSTRY

Q CELLS is the first solar module manufacturer to pass the most comprehensive quality programme in the industry: The new "Quality Controlled PV" of the independent certification institute TÜV Rheinland.

MODULES
EUROPE
2021

Q CELLS



LOW ELECTRICITY GENERATION COSTS

Higher yield per surface area, lower BOS costs and up to 30 watts more power per module.



ENDURING HIGH PERFORMANCE

Long-term yield security with Anti LID Technology, Anti PID Technology¹, Hot-Spot Protect and Traceable Quality Tra.Q™.



EXTREME WEATHER RATING

High-tech aluminum alloy frame, certified for high snow (5400 Pa) and wind loads (2400 Pa).



A RELIABLE INVESTMENT

Inclusive 12-year product warranty and 25-year linear performance warranty².



STATE OF THE ART MODULE TECHNOLOGY

Q.ANTUM DUO combines cutting edge cell separation and innovative 12-busbar design with Q.ANTUM Technology.



² See data sheet on rear for further information.




THE IDEAL SOLUTION FOR:



Ground-mounted solar power plants



*Long cables (+) ≥ 57.1 in (1450 mm), (-) ≥ 57.1 in (1450 mm) are available upon request.




ELECTRICAL CHARACTERISTICS

PO	WER CLASS			445	450	455	460	465
MIN	IIMUM PERFORMANCE AT STANDAR	D TEST CONDITIO	NS, STC1 (PO	WER TOLERANCE +	5W/-0W)			
	Power at MPP¹	P _{MPP}	[W]	445	450	455	460	465
_	Short Circuit Current ¹	I _{sc}	[A]	10.62	10.65	10.67	10.70	10.73
un u.	Open Circuit Voltage ¹	V _{oc}	[V]	53.15	53.18	53.22	53.25	53.29
Minir	Current at MPP	I _{MPP}	[A]	10.10	10.15	10.20	10.25	10.30
2	Voltage at MPP	V_{MPP}	[V]	44.06	44.34	44.61	44.89	45.16
	Efficiency ¹	η	[%]	≥20.0	≥20.2	≥20.4	≥20.6	≥20.9
MIN	IIMUM PERFORMANCE AT NORMAL	OPERATING CONI	DITIONS, NM	OT ²				
	Power at MPP	P _{MPP}	[W]	333.2	337.0	340.7	344.5	348.2
Ξ	Short Circuit Current	I _{sc}	[A]	8.56	8.58	8.60	8.62	8.64
ij	Open Circuit Voltage	V _{oc}	[V]	50.12	50.15	50.18	50.22	50.25
Ē	Current at MPP	I _{MPP}	[A]	7.95	7.99	8.03	8.08	8.12
	Voltage at MPP	V _{MPP}	[V]	41.93	42.17	42.41	42.64	42.87

¹Measurement tolerances P_{MPP} ±3%; I_{SC}; V_{OC} ±5% at STC: 1000 W/m², 25±2°C, AM 1.5 according to IEC 60904-3 • ²800 W/m², NMOT, spectrum AM 1.5


Q CELLS PERFORMANCE WARRANTY



At least 98% of nominal power during first year. Thereafter max. 0.5% degradation per year. At least 93.5% of nominal power up to 10 years. At least 86% of nominal power up to 25 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Q CELLS sales organisation of your respective country.

PERFORMANCE AT LOW IRRADIANCE



Typical module performance under low irradiance conditions in comparison to STC conditions (25 °C, 1000 W/m²)

TEMPERATURE COEFFICIENTS								
Temperature Coefficient of I _{SC}	α	[%/K]	+0.04	Temperature Coefficient of Voc	β	[%/K]	-0.27	
Temperature Coefficient of P _{MPP}	γ	[%/K]	-0.35	Nominal Module Operating Temperature	NMOT	[°F]	109±5.4 (43±3°C)	

PROPERTIES FOR SYSTEM DESIGN

	${\bf Maximum\ System\ Voltage\ V_{SYS}}$	[V]	1500 (IEC)/1500 (UL)	PV module classification	Class II
	Maximum Series Fuse Rating	[A DC]	20 Fire Rating based on ANSI/UL 61730		TYPE 1
-	Max. Design Load, Push/Pull ³	[lbs/ft ²]	75 (3600 Pa) / 33 (1600 Pa)		-40°F up to +185°F
	Max. Test Load, Push / Pull ³	[lbs/ft ²]	113 (5400 Pa)/50 (2400 Pa)	on Continuous Duty	(-40°C up to +85°C)

QUALIFICATIONS AND CERTIFICATES

PACKAGING AND TRANSPORT INFORMATION

47.1 in

1196 mm

UL 61730, CE-compliant Quality Controlled PV - TÜV Rheinland; IEC 61215:2016, IEC 61730:2016 U.S. Patent No. 9,893,215 (solar cells)

3 See Installation Manual











87.8 in

2230 mm



42.5 in

1080 mm





781 ka



24

pallets



22

pallets



modules

29

Note: Installation instructions must be followed. See the installation and operating manual or contact our technical service department for further information on approved installation and use of this product.

Hanwha Q CELLS America Inc.