Q.PEAK DUO XL-G10 SERIES



475-490 Wp | 156 Cells 21.2% Maximum Module Efficiency

MODEL Q.PEAK DUO XL-10.3/BFG



6 busbar cell technology



12 busbar cell technology



Bifacial energy yield gain of up to 20%

Bifacial Q.ANTUM solar cells with zero gap cell layout make efficient use of light shining on the module rear-side for radically improved LCOE.



Low electricity generation costs

Q.ANTUM DUO Z combines cutting edge cell separation and innovative wiring with Q.ANTUM Technology for higher yield per surface area, lower BOS costs, higher power classes, and an efficiency rate of up to 21.2%.



A reliable investment

Double glass module design enables extended lifetime with 12-year product warranty and improved 30-year performance



Enduring high performance

Long-term yield security with Anti LeTID Technology, Anti PID Technology², Hot-Spot Protect.



Frame for versatile mounting options

High-tech aluminum alloy frame protects from damage, enables use of a wide range of mounting structures and is certified regarding IEC for high snow (5400 Pa) and wind loads (2400 Pa).



Innovative all-weather technology

Optimal yields, whatever the weather with excellent low-light and temperature behavior.

- 1 See data sheet on rear for further information. 2 APT test conditions according to IEC/TS 62804-1:2015 method B (–1500 V, 168 h) including post treatment according to IEC 61215-1-1 Ed. 2.0 (CD)

The ideal solution for:










Q.PEAK DUO XL-G10 SERIES

■ Mechanical Specification

Format	87.2 in × 41.1 in × 1.38 in (including frame) (2216 mm × 1045 mm × 35 mm)
Weight	64.2 lbs (29.1kg)
Front Cover	0.08 in (2.0 mm) thermally pre-stressed glass with anti-reflection technology
Back Cover	0.08 in (2.0 mm) semi-tempered glass
Frame	Anodized aluminum
Frame Cell	Anodized aluminum 6 × 26 monocrystalline Q.ANTUM solar half cells
Cell	6 × 26 monocrystalline Q.ANTUM solar half cells 2.09-3.98 in × 1.26-2.36 in × 0.59-0.71 in



■ Electrical Characteristics

PC	OWER CLASS			475		480		485		490	
MIN	MINIMUM PERFORMANCE AT STANDARD TEST CONDITIONS, STC1 (POWER TOLERANCE +5 W/-0 W)										
					BSTC*		BSTC*		BSTC*		BSTC*
	Power at MPP ¹	P_{MPP}	[W]	475	519.6	480	525.0	485	530.5	490	536.0
finimum	Short Circuit Current ¹	I _{sc}	[A]	11.08	12.12	11.12	12.17	11.16	12.21	11.20	12.26
	Open Circuit Voltage ¹	V _{oc}	[V]	53.15	53.34	53.39	53.58	53.63	53.82	53.86	54.06
	Current at MPP	I _{MPP}	[A]	10.55	11.54	10.59	11.58	10.63	11.63	10.67	11.67
_	Voltage at MPP	V_{MPP}	[V]	45.03	45.02	45.33	45.32	45.63	45.62	45.93	45.92
	Efficiency ¹	η	[%]	≥20.5		≥20.7		≥20.9		≥21.2	

Bifaciality of P_{MPP} and I_{SC} 70% \pm 5% \bullet Bifaciality given for rear side irradiation on top of STC (front side) \bullet According to IEC 60904-1-2

 $^{1}\text{Measurement tolerances P}_{\text{MPP}} \pm 3\,\%; \text{I}_{\text{SC}}, \text{V}_{\text{OC}} \pm 5\,\% \text{ at STC: } 1000\,\text{W/m}^{2}; \text{*at BSTC: } 1000\,\text{W/m}^{2} + \phi \times 135\,\text{W/m}^{2}, \phi = 70\,\% \pm 5\,\%, 25 \pm 2\,^{\circ}\text{C}, \text{AM 1.5 according to IEC 60904-3}$ MINIMUM PERFORMANCE AT NORMAL OPERATING CONDITIONS, NMOT²

Minimum	Power at MPP	P_{MPP}	[W]	357.6	361.4	365.1	368.9	
	Short Circuit Current	I _{sc}	[A]	8.92	8.96	8.99	9.02	
	Open Circuit Voltage	V _{oc}	[V]	50.27	50.49	50.72	50.95	
	Current at MPP	I _{MPP}	[A]	8.30	8.34	8.37	8.40	
	Voltage at MPP	V _{MDD}	[V]	43.06	43.35	43.63	43.92	

²800 W/m², NMOT, spectrum AM 1.5


Qcells PERFORMANCE WARRANTY



At least 98% of nominal power during first year. Thereafter max. 0.45% degradation per year. At least 93.95% of nominal power up to 10 years. At least 84.95% of nominal power up to 30 years.

All data within measurement tolerances. Full warranties in accordance with the warranty terms of the Qcells sales organisation of your respective country.





PERFORMANCE AT LOW IRRADIANCE

Typical module performance under low irradiance conditions in comparison to STC conditions ($25\,^{\circ}$ C, $1000\,\text{W/m}^2$).

TEMPERATURE COEFFICIENTS							
Temperature Coefficient of I _{sc}	α	[%/K]	+0.04	Temperature Coefficient of $V_{\rm oc}$	β	[%/K]	-0.27
Temperature Coefficient of P _{MPP}	γ	[%/K]	-0.34	Nominal Module Operating Temperature	NMOT	[°F]	109±5.4 (43±3°C)

■ Properties for System Design

*Standard terms of guarantee for the 5 PV companies with the highest production capacity in 2021 (February 2021)

Maximum System Voltage	V_{SYS}	[V]	1500	
Maximum Series Fuse Rating		[A DC]	20	
Max. Design Load, Push/Pull ³		[lbs/ft²]	75 (3600 Pa)/33 (1600 Pa)	
Max. Test Load, Push/Pull ³		[lbs/ft²]	113 (5400 Pa)/50 (2400 Pa)	

³ See Installation Manual

PV module classification Class II TYPE 29⁴ Fire Rating based on ANSI/UL 61730 **Permitted Module Temperature** -40°F up to +185°F on Continuous Duty (-40°C up to +85°C)

⁴New Type is similar to Type 3 but with metallic frame

Qualifications and Certificates

Quality Controlled PV -TÜV Rheinland: UL 61730, CE-compliant, IEC 61215:2016. IEC 61730:2016, U.S. Patent No. 9,893,215 (solar cells)









ocells

